







Since 1759



250 years of exceptional engineering

GKN Sinter Metals Filters, the leading manufacturer of porous sinter metal products, offers a variety of solutions to fulfil customer requirements.

We are familiar with various applications in almost every industrial branch.

Our products are applied in gas- and liquid filtration, dampening, sparging, sensor protection, bulk handling and many more. We offer solutions for high temperature and corrosive environments.

Sintered filter elements made of stainless steels, bronze, nickel based alloys, titanium and several special alloys can be manufactured seamless up to 1500 mm length and 320 mm OD. Larger elements will be assembled in our certified in-house welding shop.

Our most innovative product for the chemical industry is the patented metallic membrane SIKA-R...AS.

The filter cartridges equipped with this state-of-the-art technology offer a flow rate up to 4 times higher compared to conventional sinter metal filter cartridges. Furthermore an excellent back flush performance is guaranteed. The filter active membrane layer with filter grades down to 0.1 μ m absolute has a thickness of only 200 μ m and is made of the same alloy as the coarse support material. The membrane is sinter bonded to the support and therefore cannot peel off.

Another innovation introduced by GKN is the sinter bonded joint of porous parts with solid fittings in order to avoid welding seams – the weak spot of all sintered cartridges of our competitors.

All sintered materials of GKN offer a self-supporting structure with high mechanical strength.

We manufacture various filter grades with specified pore sizes and flow rates in order to have the appropriate solution for your requirements.




SIKA-R...AX is the brand name of GKN Sinter Metals' high porous stainless filter elements manufactured by coaxial compaction

SIKA-R...AX materials are used as self-supporting structural elements. The pores are mechanically fixed regarding size and position after the sintering process.







Properties

These characteristics of SIKA-R...AX products go along with the following important properties:

- Shape/-stability i.e. selfsupporting structural elements suitable for high differential pressures
- Particularly good properties when under compression, vibration and changing conditions or with high sudden pressures peaks
- High heat resistance and thermal stability

- Defined permeability and filtration properties because the pore size and distribution are exact and uniform
- Backflushing and easy cleaning with supersaturated superheated steam, chemical solvents, thermal and ultrasonic processes
- The variety of materials used can be welded and machined





Application Examples

- Autogenous welding (as flame arrestors) / Explosion protection
- Polymer filtration
- Gas- and Liquid filtration
- Silencing
- Sparging
- Fluidization (handling of bulk material)
- Sensor and valve protection
- Flow restriction

As well as various applications in industries like

- Chemical
- Food / Beverage
- Semiconductor
- Scientific Instrumentation
- Pharmaceutical


















Various forms of sensor protection






Manufacturing of SIKA-R...AX Products

Pressing process

SIKA-R...*AX* filter elements are formed by co-axial pressing.

The metal powder is filled into the appropriate die and compacted in axial direction by upper and lower punch. The pore size of the finished product can be controlled by the choice of powder size and the pressing force used to form the part.

A wide range of finished shapes can be achieved by this pressing process.






Sintering

The compacted part is sintered in specially designed furnaces. Sintering is the fundamental processing step for all Powdered Metal (P/M) products. It is the process of bonding the powder particles by fusing them together at temperatures well below their melting point.

After sintering, regardless of micron size, the separate grain structure of the original powdered metal becomes fully interlinked to form a rigid part.


Sintering gives the high porous material the shape stability and property of a strong metal component.



Burn-out of lubricant

Sintering

Cooling





Standard Materials

Ma	terial	Name MatNo. SIKA-					Fe	Cr	Ni	С	Мо	Miscellany	Max. Temp	erature °C	Keyword				
				IS	R		FIL	В		in Gewich	ts-% / in w	eight- %	I		Reduzierend Reducing	Oxidierend Oxidizing			
		AISI 304 L	1.4306	Х	Х	Х			Bal.	18,0-20,0	8,0-12,0	<=0,03	0,5	N<=0,1	600	500	Standard for food application		
a		AISI 316 L	1.4404	Х	х	Х			Bal.	16,0-18,0	10,0-14,0	<=0,03	2,0-3,0	N<=0,1	540	400			
High alloyed material							Х								380	320			
		AISI 904 L	1.4539	Х	х	х			Bal.	19,0-21,0	24,0-26,0	<=0,02	4,0-5,0	N<=0,15 Cu 1,2-2,0	600	500	Resistant against sulphuric acid, phosphoric and hydro- chloric acid		
gha		AISI 310	1.4841	Х			Х		Bal.	24,0-26,0	19,0-22,0	<=0,25	-	-	800	600	Heat resistant		
宝		FeCrAl	1.4767 Mod.				х		Bal.	19,0-22,0	-	<0,10	-	Al 5,0-6,5 with rare earth elements	unfit	1000			
	אוכתכן ממסכם מונסץס	Hastelloy C 22	2.4602	Х					2,0-6,0	20,0-22,5	Bal.	⟨0,02	12,0-14,5	W 2,0-3,5 Co 2,5	650	650	Corrosion resistant with		
oys*		Hastelloy C 276	2.4819	Х	Х				4,0-7,0	14,0-16,0	Bal.	⟨0,02	15,0-17,0	W 3,0-4,5	650	650	various agressive media. Duration appli- cation at > 400 °C possible		
sed all		Hastelloy X	2.4665	х	х				17,0-20,0	20,5-23,0	Bal.	<0 , 15	8,0-10,0	Co 0,5-2,5 W 0,2-1,0	930	800			
el ba		Inconel 600	2.4816	Х	х	Х			6,0-10,0	14,0-17,0	>=72,0	<0,15	-	-	700	600			
Nick		Inconel 625	2.4856	Х		Х			<=5,00	20,0-23,0	>=58,0	<0,10	8,0-10,0	Nb 3,15-4,15	650	650			
_		Monel 400	2.4360	Х	Х	Х			⟨2,0	i	>=63,0	<0,30	-	Cu 28,0-34,0	500	500	Resistant against Cl-contain- ing media		
Bronze		CuSn 11	2.1052					Х	-	-	-	-	-	-	300	250	Typically used for hydraulic & pneumatic		
Tita-	nium**	Ti	-	х	х				-	-	-	-	-	Ti > 99 %	500	500	Medicine, acid, electrolysis		
Other		Other materials on request																	

^{*} Nickel based AX-products only after consultation. Not all dimensions feasible. **Not all raw materials are in stock. Typical Iron or Nickel elements e.g. Si, Mn, P, S according to the literature.

Elements SIKA-R...AX

Our various high porosity sintered metal filter elements can be manufactured in the following standard geometries:

- Discs
- Cylinders / Open ended
- Cylinders with one closed end
- Plates
- Cones
- Silencer made of stainless steel sintered together with a solid stainless steel thread

Seamless design up to 315 mm diameter.

We also manufacture to customer-specified dimensions.

Bigger elements can be welded at our certified in-house welding shop.


GKN Filter Grades

SIKA-R	0,5	AX
SIKA-R	1	AX
SIKA-R	3	AX
SIKA-R	5	AX
SIKA-R	7	AX
SIKA-R	10	AX
SIKA-R	15	AX
SIKA-R	20	AX
SIKA-R	30	AX
SIKA-R	40	AX
SIKA-R	50	AX
SIKA-R	80	AX
SIKA-R	100	AX
SIKA-R	150	AX
SIKA-R	200	AX




Standard Geometries

SIKA-Discs



Seamless construction is possible up to 315mm diameter and 40mm in height.





Standard plate size is 200 x 300 mm, height up to 20mm.




Standard Geometries

SIKA-Cylinders / Open ended






SIKA-Cylinders with one closed end





Silencer made of stainless steel sintered together with a solid stainless steel thread









Customer Specific Constructions










Additional Applications of GKN Filters...









Basic Information for Designing a Filter

Customer's Information	Company Name:				
Enquiry data.	Contact Name: Street Address:				
Enquiry date:	ZIP:				
	Town, US State:				
	Country:				
1. The planned application of the SIKA element?	Filtration	Equalizing	g 🗆	Fluidizin	g 🗆
	Separation □	Silencing		Sparging	
	Throttling □	Protecting		Degassin	ng 🗆
Others					
2. What kind of gas or liquid will flow through the SIKA elen	nent?				
Medium Specification					
Operation density					
Dynamic viscosity					
Operation temperature					
Operating flow rate					
Absolute operating pressure before SIKA-element	-				
Wanted or permissible pressure drop of clean filter					
Max permissible pressure drop of used filter					
3. Which particles must be retained by a SIKA element?					
Description					
4. How will the SIKA element be applied?					
Shape of the element		Cartridge		Sheet D]
	Disc □	Other			
Connecting Element		Thread		Other E]
Housing diameter					
4. Short description of the process:					



Further Brochures Available







GKN Sinter Metals Filters GmbH

Dahlienstraße 43 D-42477 Radevormwald P.O. Box 1520 D-42464 Radevormwald

Phone: +49 (0) 2195-609-0 Fax: +49 (0) 2195-609-48 Email: info@gkn-filters.com

www.gkn-filters.com

